

TECAFINE® HDPE - Stock Shapes (rods, plates, tubes)

Chemical Designation

PE (Polyethylene)

Colour

white translucent

Density

0.95 g/cm³

Main features

- broad chemical compatibility
- easy to machine
- good impact strength
- low moisture absorption

Target Industries

- food processing
- food engineering
- conveyor technology
- chemical technology
- automotive industry
- home appliances

Mechanical properties	condition	value		test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	140,000	psi	ASTM D 638	
Tensile strength at yield	@ 73 °F	3,700	psi	ASTM D 638	
Elongation at break	@ 73 °F	>100	%	ASTM D 638	
Flexural strength	@ 73 °F	4,000	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	140,000	psi	ASTM D 790	
Impact strength (Izod)	@ 73 °F	1.94	ft-lbs/in	ASTM D 256	
Shore hardness	D Hardness	67		ASTM D 2240	
Rockwell hardness	R Scale	54		ASTM D 785	
Thermal properties	condition	value		test method	comment
Vicat softening point		261	°F	ASTM D 1525	1) (1) publicly sourced resin data
Deflection temperature	@ 66 psi	167	°F	ASTM D 648	2) (2) publicly sourced resin data
Service temperature	Brittleness Temperature	-105	°F	-	3) (3) ASTM D 746 publicly sourced resin data
Service temperature	Long Term Max	248	°F	-	4) (4) publicly sourced resin data

→ Resin specification:
ASTM D4976-06 PE235
Shapes specification:
NONE

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Ensinger Inc. Headquarters
365 Meadowlands Boulevard
Washington, PA 15301, USA

Phone 800-243-3221 Sales
Phone 800-869-4029 Technical
Fax 724-746-9209
sales@ensinger-ind.com

Date: 2016/10/31

Version: A0