

# TECAPEEK® MT natural polyetheretherketone - Stock Shapes (rods, plates, tubes)

## Chemical Designation

PEEK (Polyetheretherketone)

## Colour

beige opaque

## Density

1.31 g/cm<sup>3</sup>

## Main features

- excellent chemical resistance
- very good stress cracking resistance
- high creep resistance
- hydrolysis and superheated steam resistant
- good machinability
- resistance against high energy radiation
- good slide and wear properties
- very good sterilisable

## Target Industries

- food technology
- mechanical engineering
- pharmaceutical industry
- medical technology

Mechanical properties	condition	value		test method	comment
Modulus of elasticity (tensile test)	1% Sec, 73 °F	650,000	psi	ASTMD 638	(1) Data obtained from public source
Tensile strength at yield	@ 73 °F	16,000	psi	ASTMD 638	(2) Injection molded specimen data obtained from public source
Tensile strength at break	@ 73 °F	8,900	psi	ASTMD 638	(3) injection molded specimen, data obtained from public source
Elongation at yield	@ 73 °F	4.9	%	ASTMD 638	
Elongation at break	@ 73 °F	30	%	ASTMD 638	
Flexural strength	@ 73 °F	26,000	psi	ASTMD 790	
Modulus of elasticity (flexural test)	@ 73 °F	600,000	psi	ASTMD 790	
Compression strength	@ 73 °F 10% strain	20,000	psi	ASTMD 695	
Compression modulus	@ 73 °F	493,000	psi	ASTMD 695	1)
Notched impact strength (Izod)	@ 73 °F	0.95	ft-lbs/in	ASTMD 256	
Rockwell hardness	M Scale	99		ASTMD 785	
Coefficient of friction	@ 68 °F Static, 40 psi	0.20		ASTMD 3702	2)
Coefficient of friction	@ 68 °F, Dynamic 40 psi 50 fpm	0.25		ASTMD 3702	3)
Wear (K) factor	40 psi, 50 fpm	200	*10 <sup>-10</sup> in <sup>3</sup> -min/ft-lb-hr	ASTMD 3702	
Thermal properties	condition	value		test method	comment
Melting temperature		633	°F	-	(1) Injection molded specimen
Deflection temperature	@264 psi	320	°F	ASTMD 648	1)
Service temperature	short term	572	°F	-	2)
Service temperature	Long Term	480	°F	-	3)
Thermal expansion (CLTE)	< Tg, along flow	2.5	*10 <sup>-5</sup> in/in/°F	DIN EN ISO 11359-1;2	4)
Thermal conductivity		2.01	BTU-in/hr-ft <sup>2</sup> -°F	ISO 22007-4:2008	5)
					(5) Injection molded specimen from public source
Electrical properties	condition	value		test method	comment
surface resistivity		1.0*10 <sup>16</sup>	Ω/square	ASTMD 257	1)
Volume resistivity	@ 73 °F	4.9*10 <sup>16</sup>	Ω*cm	ASTMD 149	2)
Dielectric strength	0.1" thick IEC 60243-1	630	V/mil	-	3)
Dissipation factor	@ 73 °F, 1 MHz	0.003		DIN IEC 60250	4)
Dielectric constant	@ 73 °F, 1 kHz	2.8		DIN IEC 60250	5)
					(5) injection molded data from public source
Other properties	condition	value		test method	comment
Limiting PV		69000	psi-fpm	ASTMD 3702	1)
Moisture absorption	@ saturation, 73 °F	0.45	%	DIN EN ISO 62	2)
Moisture absorption	@ 24 hrs, 73 °F	0.02	%	ASTMD 570	(3) Injection molded specimen 3.0mm
Flammability (UL94)		V0		-	3)

→ Resin specification:  
ASTM D4000-11 PEEK; MIL-P-46183 Ty. I  
Shapes specification:  
ASTM D6262-12 S-PAEK0111

→ TECAPEEK products are based on Victrex® PEEK polymer.

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com).

---

**Ensinger Inc. Headquarters**  
365 Meadowlands Boulevard  
Washington, PA 15301, USA

Phone 800-243-3221 Sales  
Phone 800-869-4029 Technical  
Fax 724-746-9209  
[sales@ensinger-ind.com](mailto:sales@ensinger-ind.com)

Date: 2020/09/11

Version: A2