

TECASON® P black (Radel 5500) - Stock Shapes (rods, plates, tubes)

Chemical Designation
PPSU (Polyphenylsulfone)

Colour
black

Density
1.29 g/cm³

Main features

- high strength
- high thermal and mechanical capacity
- very resistant to autoclaving
- high dielectric strength
- good machinability

Target Industries

- medical technology
- electronics
- food processing
- process engineering

Mechanical properties	condition	value		test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	340,000	psi	ASTM D 638	(1) data obtained from public source
Tensile strength at yield	@ 73 °F	11,500	psi	ASTM D 638	
Elongation at break	@ 73 °F	60	%	ASTM D 638	
Flexural strength	@ 73 °F	13,200	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	350,000	psi	ASTM D 790	
Compression strength	@ 73 °F, 1% strain	1990	psi	ASTM D 695	
Compression strength	@ 73 °F, 10% strain	14,350	psi	ASTM D 695	1)
Compression modulus	@ 73 °F	234,000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	3	ft-lbs/in	ASTM D 256	
Rockwell hardness	@ 73 °F, M scale	96		ASTM D 785	
Rockwell hardness	@ 73 °F, R Scale	123		ASTM D 785	
Thermal properties	condition	value		test method	comment
Vicat softening point		424	°F	-	1)
Deflection temperature	@264 psi	405	°F	ASTM D 648	2)
Service temperature	Intermittent	360	°F	-	3)
Service temperature	Long Term	300	°F	-	3)
Thermal expansion (CLTE)		3.1* 10 ⁻⁵	in/in/°F	ASTM D 696	4)
Specific heat		0.27	BTU/lb-F°	-	5)
Thermal conductivity		1.74	BTU-in/hr-ft ² -°F	-	6)
Electrical properties	condition	value		test method	comment
Volume resistivity		9*10 ¹⁵	Ω*cm	ASTM D 257	1)
Dielectric strength	thickness 0.125"	381	V/mil	ASTM D 149	2)
Dielectric constant	@ 60 Hz, 73 °F, 50% RH	3.44		ASTM D 150	3)
Other properties	condition	value		test method	comment
Moisture absorption	@ 24 hrs, 73 °F	0.37	%	ASTM D 570	(1) injection molded sample thickness greater than 0.790 mm
Moisture absorption	@ saturation, 73 °F	1.1	%	ASTM D 570	
Flammability (UL94)		V0		-	1)

→ Resin specification:
ASTM D 6394-10 SP0311
Shapes specification:
NONE

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.