

TECAST® T natural - Stock Shapes (rods, plates, tubes)

Chemical Designation

PA 6 (Polyamide 6)

Colour

natural white

Density

1.14 g/cm³

Main features

- good wear properties
- good mechanical properties
- high fatigue strength
- good damping
- high mechanical load capacity
- resistant to many oils, greases and fuels

Target Industries

- construction industry
- gear manufacturing
- oil and gas industry
- conveyor technology
- agricultural machinery
- heavy duty industry
- food engineering
- food processing
- mining industry

Mechanical properties	condition	value		test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	400,000	psi	ASTM D 638	(1) Data obtained from public source
Tensile strength at yield	@ 73 °F	12,000	psi	ASTM D 638	(2) Data obtained from public source
Elongation at yield	@ 73 °F	4	%	ASTM D 638	(3) Data obtained from public source
Elongation at break	@ 73 °F	30	%	ASTM D 638	
Flexural strength	@ 73 °F	12,500	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	350,000	psi	ASTM D 790	
Compression strength	@ 1% strain	3,400	psi	ASTM D 695	
Compression strength	@ 10% strain	14,400	psi	ASTM D 695	
Compression modulus	@ 73 °F	360,000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	1.4	ft-lbs/in	ASTM D 256	
Rockwell hardness	@ 73 °F R Scale	120		ASTM D 785	
Coefficient of friction	Dynamic, 40 psi, 50 fpm	0.26		ASTM D 3702	2)
Wear (K) factor	Against Steel, 40 psi, 50 fpm	200*10 ⁻⁷	in ³ -min/ft-lbs-hr	ASTM D 3702	3)
Thermal properties	condition	value		test method	comment
Melting temperature		428	°F	ASTM D 2133	(1) Data obtained from public source
Deflection temperature	@ 264 psi	200	°F	ASTM D 648	(2) Data obtained from public source
Deflection temperature	@ 66 psi	370	°F	ASTM D 648	(3) Data obtained from public source
Service temperature	Intermittent	300	°F	-	
Service temperature	Long Term	200	°F	-	
Thermal expansion (CLTE)		4.0	*10 ⁻⁵ in/in/°F	ASTM D 696	3)
Specific heat		0.40	BTU/lb-F°	-	
Thermal conductivity		1.67	BTU-in/hr-ft ² -°F	-	
Electrical properties	condition	value		test method	comment
surface resistivity		1.0*10 ¹⁴	Ω/square	ASTM D 257	1) (1) Data obtained from public source
volume resistivity		10 ¹⁴	Ω*cm	ASTM D 257	2) (2) Data obtained from public source
Dielectric strength		500	V/mil	ASTM D 149	
Dielectric constant	@ 60 Hz, 73 °F, 50% RH	3.7		ASTM D 150	
Other properties	condition	value		test method	comment
Moisture absorption	@ saturation, 73°F	5.5	%	ASTM D 570	1) (1) Data obtained from public source
Moisture absorption	@ 24 hrs, 73 °F	1.2	%	ASTM D 570	2) (2) estimated
Flammability (UL94)		HB		-	2)

→ Resin specification:

Shapes specification:
ASTM D5989-11 S-PA0211

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.