

TECASINT 2021 black - Stock Shapes (rods, plates, tubes)

Chemical Designation

PI (Polyimide)

Colour

black

Density

1.46 g/cm³

Fillers

15% graphite

Main features

- very good slide and wear properties
- very good thermal stability
- high thermal and mechanical capacity
- good chemical resistance
- resistance against high energy radiation
- high creep resistance
- sensitive to hydrolysis in higher thermal range

Target Industries

- automotive industry
- aircraft and aerospace technology
- cryogenic engineering
- conveyor technology
- hot glass technology
- mechanical engineering
- precision engineering

<i>Mechanical properties</i>	<i>condition</i>	<i>value</i>		<i>test method</i>	<i>comment</i>
Modulus of elasticity (tensile test)	@ 73 °F	638,000	psi	ASTM D 638	
Tensile strength at yield	@ 73 °F	14,645	psi	ASTM D 638	
Elongation at break	@ 73 °F	3.7	%	ASTM D 638	
Flexural strength	@ 73 °F	20,700	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	587,000	psi	ASTM D 790	
Impact strength (Charpy)	@ 73 °F, notched	17.5	ft-lbs/in	DIN EN ISO 179-1eA	
<i>Thermal properties</i>	<i>condition</i>	<i>value</i>		<i>test method</i>	<i>comment</i>
Deflection temperature	@264 psi	>600	°F	ASTM D 648	
Service temperature	Intermittent	626	°F	-	
Service temperature	Long Term	536	°F	-	
Thermal expansion (CLTE)		2.3*10 ⁻⁵	in/in/°F	ASTM D 696	
<i>Other properties</i>	<i>condition</i>	<i>value</i>		<i>test method</i>	<i>comment</i>
Moisture absorption	@ 24 hrs, 73 °F	0.44	%	ASTM D 570	
Flammability (UL94)		V0		-	

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Ensinger Inc. Headquarters
365 Meadowlands Boulevard
Washington, PA 15301, USA

Phone 800-243-3221 Sales
Phone 800-869-4029 Technical
Fax 724-746-9209
sales@ensinger-ind.com

Date: 2017/03/30

Version: A0